


# OptiLite 75 Xtra

## OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	76 %	69 %
Visible Light Reflected (Int)	9 %	17 %
Visible Light Reflected (Ext)	9 %	15 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	8 %	10 %
Total Solar Energy Transmitted	39 %	34 %
Total Solar Energy Absorbed	53 %	56 %
Emissivity (Room Side)	0.84	0.84
Glare Reduction	16 %	15 %
Shading Coefficient	0.62	0.50
Solar Heat Gain Coeff. (G-Value)	0.54	0.43
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	1.20	1.38
Total Solar Energy Rejected	46 %	57 %

R09275X - OptiLite 75 Xtra Pressure Sensitive Adhesive



Ed-A DS No 1446 August 2011