

PolyZone 6 mil Anti-Graffiti

Anti-Graffiti Film for Application to Rigid Plastic Glazing

MECHANICAL PROPERTIES

Thickness	6 mil
Tensile Strength at Break	28,000 PSI
Break Strength	125 lb/inch
Elongation at Break	150 %
Peel Strength	1-2 lb/inch

OPTICAL & SOLAR PROPERTIES

	3mm Single
Visible Light Transmitted	88%
Visible Light Reflected (Int)	10%
Visible Light Reflected (Ext)	10%
Ultra Violet Block	99%
Total Solar Energy Reflected	9%
Total Solar Energy Transmitted	79%
Total Solar Energy Absorbed	11%
Glare Reduction	2%
Shading Coefficient	0.95
Solar Heat Gain Coeff. (G-Value)	0.82
U-Value Winter (IP)	1.07
U-Value Winter (SI)	6.05
Total Solar Energy Rejected	18%

R1731XP PS

Ed-D DS No 1907, March 2012

safety & security



PolyZone 6 mil Anti-Graffiti