


Natura 28

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	31 %	29 %
Visible Light Reflected (Int)	9 %	10 %
Visible Light Reflected (Ext)	14 %	21 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	15 %	19 %
Total Solar Energy Transmitted	33 %	28 %
Total Solar Energy Absorbed	52 %	53 %
Emissivity (Room Side)	0.87	0.87
Glare Reduction	65 %	65 %
Shading Coefficient	0.56	0.66
Solar Heat Gain Coeff. (G-Value)	0.48	0.58
U-Value Winter (IP)	1.05	0.48
U-Value Winter (SI)	6.00	2.75
Luminous Efficacy	0.55	0.44
Total Solar Energy Rejected	52 %	42 %

R069L8W - Natura 28 Water Activated Adhesive

WERS and NFRC pending



Energy Savings

energy efficiency

solar zone e e

Hanita Coatings