

10 Mil PerLite Safe 35

Premium Ceramic Safety Films

MECHANICAL PROPERTIES

Thickness	10 mil
Tensile Strength at Break	28,500 PSI
Break Strength	270 lb/inch
Elongation at Break	125%
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	40%
Visible Light Reflected	17%
Ultra Violet Block	99%
Total Solar Energy Reflected	18%
Total Solar Energy Transmitted	30%
Total Solar Energy Absorbed	52%
Shading Coefficient	0.53
Total Solar Energy Rejected	54%

R270L5T

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Automotive DS No 1225, February 2015

