

Sigma Pro 05

Non-Reflective Films

OPTICAL & SOLAR PROPERTIES

| | |
|--------------------------------|-------|
| Visible Light Transmitted | 5% |
| Visible Light Reflected | 6% |
| Ultra Violet Block | 99.7% |
| Total Solar Energy Reflected | 6% |
| Total Solar Energy Transmitted | 22% |
| Total Solar Energy Absorbed | 72% |
| Shading Coefficient | 0.49 |
| Total Solar Energy Rejected | 58% |

R058P0A



Powered by
NanoTechnology

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Automotive, DS No 1437, July 2015

automotive

solar zone



Hanita Coatings