

Sigma Pro 15

Non-Reflective Films

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	16%
Visible Light Reflected	7%
Ultra Violet Block	>99%
Total Solar Energy Reflected	7%
Total Solar Energy Transmitted	34%
Total Solar Energy Absorbed	59%
Glare Reduction	82%
Shading Coefficient	0.59
Total Solar Energy Rejected	49%

R058P8A



Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Sigma Pro 15 : Automotive, DS No 1438, March 2016

automotive

solar zone




Hanita Coatings