

Sigma Pro 36

Non-Reflective Films

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	36%
Visible Light Reflected	6%
Ultra Violet Block	99.7%
Total Solar Energy Reflected	6%
Total Solar Energy Transmitted	45%
Total Solar Energy Absorbed	49%
Shading Coefficient	0.67
Total Solar Energy Rejected	41%

R058P5A



Powered by
NanoTechnology

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Automotive, DS No 1441, July 2015

automotive

solar zone



Hanita Coatings