

# Sigma Pro 50

Non-Reflective Films

## OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	50%
Visible Light Reflected	7%
Ultra Violet Block	99.7%
Total Solar Energy Reflected	7%
Total Solar Energy Transmitted	54%
Total Solar Energy Absorbed	39%
Shading Coefficient	0.73
Total Solar Energy Rejected	36%

R058P7A



Powered by  
NanoTechnology

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Automotive, DS No 1442, July 2015

automotive

solar zone



Hanita Coatings