


OptiShade 35

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	35 %	32 %
Visible Light Reflected (Int)	10 %	11 %
Visible Light Reflected (Ext)	13 %	20 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	14 %	18 %
Total Solar Energy Transmitted	34 %	29 %
Total Solar Energy Absorbed	53 %	53 %
Emissivity (Room Side)	0.86	0.86
Glare Reduction	61 %	61 %
Shading Coefficient	0.58	0.67
Solar Heat Gain Coeff. (G-Value)	0.5	0.59
U-Value Winter (IP)	1.05	0.48
U-Value Winter (SI)	5.97	2.75
Luminous Efficacy	0.6	0.47
Total Solar Energy Rejected	50 %	41 %

R06903W - OptiShade 35 Water Activated Adhesive



ED-A_DS No 1003 May 2015