


SolarZoneXTRM PolyZone SkyLite

Film for Application to Rigid Plastic Glazing

OPTICAL & SOLAR PROPERTIES

	Single Pane
Visible Light Transmitted	15 %
Visible Light Reflected (Int)	63 %
Visible Light Reflected (Ext)	66 %
Ultra Violet Block	99.9 %
Total Solar Energy Reflected	64 %
Total Solar Energy Transmitted	10 %
Total Solar Energy Absorbed	26 %
Emissivity (Room Side)	0.84
Glare Reduction	84 %
Shading Coefficient	0.20
Solar Heat Gain Coeff. (G-Value)	0.17
U-Value Winter (IP)	1.03
U-Value Winter (SI)	5.85
Luminous Efficacy	0.72
Total Solar Energy Rejected	83 %

R157X5P - SolarZoneXTRM PolyZone SkyLite S20X
Pressure Sensitive Adhesive



Single pane
Energy Savings



Ed-A DS No 1449 February 2013

energy efficiency

solar zone XTRM

Hanita Coatings