

10 Mil PerLite Safe 50

Premium Ceramic Safety Films

MECHANICAL PROPERTIES

Thickness	10 mil
Tensile Strength at Break	28,500 PSI
Break Strength	245 lb/inch
Elongation at Break	125%
Peel Strength	7 lb/inch

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	52%
Visible Light Reflected	16%
Ultra Violet Block	99%
Total Solar Energy Reflected	17%
Total Solar Energy Transmitted	43%
Total Solar Energy Absorbed	40%
Shading Coefficient	0.64
Total Solar Energy Rejected	45%

R269L3T

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Automotive DS No 1238, February 2015

