

## 4 mil Alpha Plus Safe 36

### MECHANICAL PROPERTIES

Thickness	4 mil
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	5-7 lb/inch

### OPTICAL & SOLAR PROPERTIES

	6mm Single
Visible Light Transmitted	35%
Visible Light Reflected	7%
Ultra Violet Block	99%
Total Solar Energy Reflected	8%
Total Solar Energy Transmitted	39%
Total Solar Energy Absorbed	53%
Shading Coefficient	0.64
Total Solar Energy Rejected	44%

R125H5A PS

EG-E DS No 1411, July 2006